

Environmental product declaration

in accordance with ISO 14025 and EN 15804+A2

JACKOPOR EPS SWEDEN





The Norwegian EPD Foundation

Owner of the declaration:

Bewi Insulation Scandinavia

Product:

JACKOPOR EPS SWEDEN

Declared unit:

1 m2

This declaration is based on Product Category Rules:

CEN Standard EN 15804:2012+A2:2019 serves as core

NPCR 012:2022 Part B for thermal insulation products

Program operator:

The Norwegian EPD Foundation

Declaration number:

NEPD-4298-3533-EN

Registration number:

NEPD-4298-3533-EN

Issue date: 22.03.2023

Valid to: 22.03.2028

Ver-070723



General information

Product

JACKOPOR EPS SWEDEN

Program operator:

Post Box 5250 Majorstuen, 0303 Oslo, Norway The Norwegian EPD Foundation Phone: +47 23 08 80 00 web: post@epd-norge.no

Declaration number: NEPD-4298-3533-EN

This declaration is based on Product Category Rules:

CEN Standard EN 15804:2012+A2:2019 serves as core PCR NPCR 012:2022 Part B for thermal insulation products

Statement of liability:

The owner of the declaration shall be liable for the underlying information and evidence. EPD Norway shall not be liable with respect to manufacturer information, life cycle assessment data and evidences.

Declared unit:

1 m2 JACKOPOR EPS SWEDEN

Declared unit with option:

A1,A2,A3,A4,A5,C1,C2,C3,C4,D

Declared unit, specification:

1 $\mathrm{m^2}$ Jackopor 80 EPS insulation board with 38 mm thickness at R=1 $\mathrm{m^2}$

K/W, transportation to site, waste handling and recovery.

General information on verification of EPD from EPD tools:

Independent verification of data, other environmental information and the declaration according to ISO 14025:2010, § 8.1.3 and § 8.1.4. Verification of each EPD is made according to EPD-Norway's guidelines for verification and approval requiring that tools are i integrated into the company's environmental management system, ii the procedures for use of the EPD tool are approved by EPD-Norway, and iii the process is reviewed annually by an independent third party verifier. See Appendix G of EPD-Norway's General Programme Instructions for further information on EPD tools

Verification of EPD tool:

Independent third party verification of the EPD tool, background data and test-EPD in accordance with EPDNorway's procedures and guidelines for verification and approval of EPD tools.

Third party verifier:

Elisabet Amat

(no signature required

Owner of the declaration:

Bewi Insulation Scandinavia Contact person: Svein Tore Larsen Phone: +47 95 07 67 42 e-mail: svein.tore.larsen@jackon.no

Manufacturer:

Bewi Insulation Scandinavia AB Diabasvägen 11 SE-541 52 Skövde, Sweden

Place of production:

Bewi Insulation Scandinavia, Skövde Diabasvägen 6 SE-541 52 Skövde, Sweden

Management system:

ISO 9001: 185977-2015-AQ-NOR-NA and ISO 14001: 251411-2017-AE-NOR-NA

Organisation no:

913019334

Issue date: 22.03.2023

Valid to: 22.03.2028

Year of study:

2021

Comparability:

EPD of construction products may not be comparable if they not comply with EN 15804 and seen in a building context.

Development and verification of EPD:

The declaration is created using EPD tool lca.tools ver EPD2022.03, developed by LCA.no. The EPD tool is integrated in the company's management system, and has been approved by EPD Norway.

Developer of EPD: Mikael Danestedt

Reviewer of company-specific input data and EPD: Svein Tore Larsen

Approved:

Håkon Hauan Managing Director of EPD-Norway



Product

Product description:

Product variation and calculation of averages

The insulation board is provided in several dimensions and thicknesses. Please use the conversion table below for other sizes than the declared unit

No variation between sites; single production site declared.

Product description

Expanded polystyrene (EPS) is a common material used for thermal insulation of buildings, including floors, walls and ceilings. It is a polymer foam, consisting of air-filled polystyrene cells. As 98% of the material is air, EPS provides good insulating properties at a low weight. Other characteristics of the material include low moisture absorption, long service life and high compressive strength.

EPS is manufactured through permeating polystyrene beads with pentane, allowing the beads to expand when exposed to steam. This addition of a so-called blowing agent adds 4% - 6% w/w. The expanded polystyrene (EPS) beads are then fed into a block molding machine, where steam and pressure forms large blocks of EPS. The amount of EPS going into the mold determines the densitiy of the block, where pressure class 80 provides a density at 80 kN/m2, which is approximately 15 kg/m3. After molding, the remaining blowing agent, pentane, is aired out and the blocks are cut into the desired shape.

Weight per declared unit is 0,57 kg given a density of 15 kg/cubic meter with a thickness of 38 mm.

Product specification

Density:

60: 13,0 kg/m3 80: 15,0 kg/m3

100: 17,5 kg/m3

150: 23,5 kg/m3

200: 28,5 kg/m3

300: 39,5 kg/m3

Materials	kg	%
Plastic - Polystyrene expandable (EPS)	0,57	99,34
Packaging - EPS	0,00	0,66
Total	0,57	
Packaging	kg	%
Packaging - Plastic	0.01	100,00
Total incl. packaging	0,58	. 2 3/00

Technical data:

CE marking: EPS insulation boards are CE certified according to SS-EN 13163

Typical size: 600 mm x 1200 mm, 1200 x 2400mm

Typical thickness: 10 mm - 400 mm Moisture absoprtion: < 5 vol%

Fire Class: F

Market:

Sweden

Reference service life, product

As in the construction where it is used

Reference service life, building or construction works

As in the construction where it is used

LCA: Calculation rules

Declared unit:

1 m2 JACKOPOR EPS SWEDEN

Cut-off criteria:

All major raw materials and all the essential energy is included. The production processes for raw materials and energy flows with very small amounts (less than 1%) are not included. These cut-off criteria do not apply for hazardous materials and substances.

Allocation:

The allocation is made in accordance with the provisions of EN 15804. Incoming energy and water and waste production in-house is allocated equally among all products through mass allocation. Effects of primary production of recycled materials is allocated to the main product in which the material was used. The recycling process and transportation of the material is allocated to this analysis.

Data quality:



Specific data for the product composition are provided by the manufacturer. The data represent the production of the declared product and were collected for EPD development in the year of study. Background data is based on EPDs according to EN 15804 and different LCA databases. The data quality of the raw materials in A1 is presented in the table below.


Materials	Source	Data quality	Year
Packaging - Plastic	ecoinvent 3.6	Database	2019
Packaging - EPS	Plastics Europe + ecoinvent 3.6	European average.	2019
Plastic - Polystyrene expandable (EPS)	Plastics Europe + ecoinvent 3.6	European average.	2019



System boundaries (X=included, MND=module not declared, MNR=module not relevant)

	P	roduct stag	je		ruction ion stage					End of life stage			Beyond the system boundaries				
	Raw materials	Transport	Manufacturing	Transport	Assembly	Use	Maintenance	Repair	Replacement	Refurb ishment	Operational energy use	Operational water use	De- construction demolition	Transport	Waste processing	Disposal	Reuse-Recovery- Recycling-potential
Ì	A1	A2	A3	A4	A5	B1	B2	В3	B4	B5	В6	В7	C1	C2	C3	C4	D
	Χ	Χ	X	Х	Χ	MND	MND	MND	MND	MND	MND	MND	Χ	Χ	Χ	X	X

System boundary:



Kvalitet	38 mm	50 mm	100 mm	150 mm	200 mm	Kubikk
80	1,00	1,32	2,63	3,95	5,26	26,32
60	0,87	1,14	2,28	3,43	4,57	21,16
100	1,16	1,53	3,06	4,59	6,13	31,46
150	1,56	2,05	4,10	6,15	8,20	44,54
200	1,89	2,48	4,97	7,45	9,93	55,50
300	2,60	3,43	6,85	10,28	13,71	76,60

Additional technical information:



LCA: Scenarios and additional technical information

The following information describe the scenarios in the different modules of the EPD.

Transport from production place to user (A4)	Capacity utilisation (incl. return) %	Distance (km)	Fuel/Energy Consumption	Unit	Value (Liter/tonne)
Truck, 16-32 tonnes, EURO 6 (kgkm)	36,7 %	100	0,043	l/tkm	4,30
Assembly (A5)	Unit	Value			
Waste, packaging, plastic to average treatment - A5 (inkl transport) (kg)	kg	0,01			
De-construction demolition (C1)	Unit	Value			
Manual demolition of EPS in C1	kg/DU	0,57			
Transport to waste processing (C2)	Capacity utilisation (incl. return) %	Distance (km)	Fuel/Energy Consumption	Unit	Value (Liter/tonne)
Truck, over 32 tonnes, EURO 6 (kgkm) - RER	53,3 %	20	0,023	l/tkm	0,46
Waste processing (C3)	Unit	Value			
Waste, Polystyrene, incineration	kg	0,57			
Disposal (C4)	Unit	Value			
Landfilling of ashes from incineration of PS	kg	0,00			
Benefits and loads beyond the system boundaries (D)	Unit	Value			
substitution of electricity, Norway	MJ	0,33			
Substitution of thermal energy, Norway (MJ)	MJ	18,20			



LCA: Results

The LCA results are presented below for the declared unit defined on page 2 of the EPD document.

Envir	onmental imp	act										
	Indicator	Unit	A1	A2	A3	A4	A5	C1	C2	C3	C4	D
	GWP-total	kg CO ₂ - eq	1,33E+00	3,76E-02	1,09E-01	9,50E-03	8,95E-04	0,00E+00	1,01E-03	1,82E+00	8,86E-05	-1,03E-01
	GWP-fossil	kg CO ₂ - eq	1,33E+00	3,76E-02	1,04E-01	9,50E-03	8,95E-04	0,00E+00	1,01E-03	1,82E+00	8,85E-05	-9,98E-02
	GWP-biogenic	kg CO ₂ - eq	5,55E-03	1,61E-05	2,15E-03	3,93E-06	1,24E-07	0,00E+00	4,34E-07	1,25E-05	4,70E-08	-5,99E-05
	GWP-luluc	kg CO ₂ - eq	3,16E-04	1,15E-05	3,65E-03	3,38E-06	6,86E-08	0,00E+00	3,09E-07	1,99E-06	1,36E-08	-3,61E-03
٥	ODP	kg CFC11 - eq	7,33E-10	9,07E-09	2,77E-08	2,15E-09	5,40E-11	0,00E+00	2,44E-10	1,30E-09	1,00E-11	-7,69E-03
	АР	mol H+ -eq	2,35E-03	1,24E-04	3,72E-04	2,73E-05	1,10E-06	0,00E+00	3,26E-06	2,16E-04	3,12E-07	-8,25E-04
	EP-FreshWater	kg P -eq	5,47E-06	2,99E-07	3,83E-06	7,59E-08	1,84E-09	0,00E+00	8,06E-09	1,29E-07	1,20E-09	-8,97E-06
	EP-Marine	kg N -eq	6,26E-04	2,71E-05	6,58E-05	5,40E-06	1,01E-06	0,00E+00	7,14E-07	1,04E-04	9,73E-08	-2,79E-04
	EP-Terrestial	mol N - eq	6,80E-03	3,03E-04	8,41E-04	6,04E-05	3,95E-06	0,00E+00	7,96E-06	1,11E-03	1,11E-06	-3,01E-03
	POCP	kg NMVOC -eq	2,97E-03	1,18E-04	6,91E-03	2,31E-05	1,30E-06	0,00E+00	3,13E-06	2,67E-04	3,06E-07	-8,30E-04
	ADP- minerals&metals ¹	kg Sb - eq	5,29E-07	6,69E-07	2,27E-06	2,62E-07	4,76E-09	0,00E+00	1,80E-08	5,61E-08	4,96E-10	-6,23E-07
	ADP-fossil ¹	MJ	4,52E+01	6,11E-01	6,60E+00	1,44E-01	3,69E-03	0,00E+00	1,64E-02	1,11E-01	8,05E-04	-1,43E+00
<u>%</u>	WDP ¹	m ³	1,05E+00	4,68E-01	6,68E+02	1,39E-01	1,30E-02	0,00E+00	1,26E-02	2,47E-01	8,35E-03	-5,19E+00

GWP-total = Global Warming Potential total; GWP-fossil = Global Warming Potential fossil fuels; GWP-biogenic = Global Warming Potential biogenic; GWP-luluc = Global Warming Potential land use and land use change; ODP = Depletion potential of the stratospheric ozone layer; AP = Acidification potential, Accumulated Exceedance; EP-freshwater = Eutrophication potential, fraction of nutrients reaching freshwater end compartment: EP-marine = Eutrophication potential, fraction of nutrients reaching marine end compartment; EP-terrestrial = Eutrophication potential, Accumulated Exceedance; POCP = Formation potential of tropospheric ozone; ADP-minerals&metals = Abiotic depletion potential for non-fossil resources; ADP-fossil = Abiotic depletion for fossil resources potential; WDP = Water (user) deprivation potential, deprivation-weighted water consumption

Remarks to environmental impacts

[&]quot;Reading example: 9,0 E-03 = 9,0*10-3 = 0,009"

^{*}INA Indicator Not Assessed

^{1.} The results of this environmental impact indicator shall be used with care as the uncertainties on these results are high or as there is limited experienced with the indicator



Addi	tional e	environmental i	mpact indi	cators								
Ind	licator	Unit	A1	A2	A3	A4	A5	C1	C2	C3	C4	D
	PM	Disease incidence	1,83E-08	3,45E-09	2,69E-09	5,81E-10	2,00E-11	0,00E+00	9,30E-11	9,10E-10	4,00E-12	-5,24E-08
	IRP ²	kgBq U235 -eq	2,86E-02	2,67E-03	2,26E-01	6,27E-04	1,67E-05	0,00E+00	7,19E-05	1,86E-04	3,82E-06	-8,22E-03
	ETP-fw ¹	CTUe	2,16E+02	4,46E-01	3,51E+00	1,06E-01	3,52E-03	0,00E+00	1,20E-02	2,69E-01	1,48E-03	-7,85E+00
40.± ****	HTP-c ¹	CTUh	5,18E-10	0,00E+00	1,02E-10	0,00E+00	0,00E+00	0,00E+00	0,00E+00	7,60E-11	0,00E+00	-1,33E-10
80 B	HTP-nc ¹	CTUh	2,31E-08	4,32E-10	2,48E-09	1,16E-10	3,00E-12	0,00E+00	1,20E-11	3,02E-09	3,00E-12	-7,47E-09
	SQP ¹	dimensionless	1,35E+00	6,99E-01	2,92E+00	1,00E-01	6,44E-03	0,00E+00	1,89E-02	1,33E-02	2,22E-03	-1,01E+01

PM = Particulate Matter emissions; IRP = Ionizing radiation – human health; ETP-fw = Eco toxicity – freshwater; HTP-c = Human toxicity – cancer effects; HTP-nc = Human toxicity – non cancer effects; SQP = Potential Soil Quality Index (dimensionless)

[&]quot;Reading example: 9,0 E-03 = 9,0*10-3 = 0,009"

^{*}INA Indicator Not Assessed

^{1.} The results of this environmental impact indicator shall be used with care as the uncertainties on these results are high or as there is limited experienced with the indicator

^{2.} This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor due to radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, from radon and from some construction materials is also not measured by this indicator.



Resource	e use											
	licator	Unit	A1	A2	A3	A4	A5	C1	C2	C3	C4	D
or G	PERE	MJ	2,75E-01	7,67E-03	3,17E+00	2,06E-03	9,32E-05	0,00E+00	2,07E-04	3,20E-03	4,69E-05	-8,31E+00
4	PERM	MJ	0,00E+00									
F3	PERT	MJ	2,75E-01	7,67E-03	3,17E+00	2,06E-03	9,32E-05	0,00E+00	2,07E-04	3,20E-03	4,69E-05	-8,31E+00
	PENRE	MJ	2,94E+01	6,11E-01	6,61E+00	1,44E-01	3,69E-03	0,00E+00	1,64E-02	1,11E-01	8,06E-04	-1,43E+00
Å	PENRM	МЈ	1,88E+01	0,00E+00								
IA	PENRT	MJ	4,82E+01	6,11E-01	6,61E+00	1,44E-01	3,69E-03	0,00E+00	1,64E-02	1,11E-01	8,06E-04	-1,43E+00
	SM	kg	1,24E-04	0,00E+00	9,27E-05	0,00E+00	1,17E-06	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00
2	RSF	MJ	3,83E-03	2,68E-04	1,23E-02	7,35E-05	2,44E-06	0,00E+00	7,24E-06	8,94E-05	1,17E-06	-8,39E-04
<u>M</u>	NRSF	MJ	2,12E-04	8,97E-04	3,88E-02	2,63E-04	6,40E-06	0,00E+00	2,43E-05	0,00E+00	1,86E-04	-5,51E-01
&	FW	m ³	3,76E-02	6,94E-05	7,91E-03	1,54E-05	1,95E-06	0,00E+00	1,87E-06	3,15E-04	7,40E-07	-3,68E-03

PERE = Use of renewable primary energy excluding renewable primary energy resources used as raw materials; PERM = Use of renewable primary energy resources used as raw materials; PERT = Total use of renewable primary energy resources; PENRE = Use of non renewable primary energy resources used as raw materials; PENRM = Use of non renewable primary energy resources; SM = Use of secondary materials; PENRM = Use of renewable secondary fuels; NRSF = Use of non-renewable secondary fuels; FW = Net use of fresh water

[&]quot;Reading example: 9,0 E-03 = 9,0*10-3 = 0,009" *INA Indicator Not Assessed



ı	End of lif	fe - Waste											
	Ind	icator	Unit	A1	A2	A3	A4	A5	C1	C2	C3	C4	D
		HWD	kg	1,85E-03	3,34E-05	2,18E-03	7,40E-06	9,67E-07	0,00E+00	9,00E-07	0,00E+00	1,47E-03	-2,08E-05
	Ū	NHWD	kg	2,84E-02	5,30E-02	2,38E-02	6,98E-03	7,52E-03	0,00E+00	1,43E-03	0,00E+00	7,28E-04	-2,96E-02
	8	RWD	kg	9,79E-07	4,17E-06	9,93E-05	9,78E-07	1,65E-08	0,00E+00	1,12E-07	0,00E+00	4,86E-09	-7,20E-06

HWD = Hazardous waste disposed; NHWD = Non-hazardous waste disposed; RWD = Radioactive waste disposed

"Reading example: 9,0 E-03 = 9,0*10-3 = 0,009" *INA Indicator Not Assessed

En	d of life	- Outpu	t flow										
	Indica	ator	Unit	A1	A2	A3	A4	A5	C1	C2	C3	C4	D
	@ D	CRU	kg	0,00E+00									
	\$\	MFR	kg	3,98E-05	0,00E+00	6,02E-03	0,00E+00	5,77E-03	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00
	DF	MER	kg	9,47E-06	0,00E+00	6,52E-08	0,00E+00	2,07E-07	0,00E+00	0,00E+00	5,70E-01	0,00E+00	0,00E+00
	5D	EEE	MJ	1,79E-04	0,00E+00	6,90E-03	0,00E+00	4,75E-05	0,00E+00	0,00E+00	1,00E+00	0,00E+00	0,00E+00
	DI	EET	MJ	2,71E-03	0,00E+00	1,04E-01	0,00E+00	7,19E-04	0,00E+00	0,00E+00	1,52E+01	0,00E+00	0,00E+00

CRU = Components for re-use; MFR = Materials for recycling; MER = Materials for energy recovery; EEE = Exported energy electrical; EET = Exported energy thermal

"Reading example: 9,0 E-03 = 9,0*10-3 = 0,009" *INA Indicator Not Assessed

Biogenic Carbon Content										
Indicator	Unit	At the factory gate								
Biogenic carbon content in product	kg C	0,00E+00								
Biogenic carbon content in accompanying packaging	kg C	0,00E+00								

Note: 1 kg biogenic carbon is equivalent to 44/12 kg CO2



Additional requirements

Greenhouse gas emissions from the use of electricity in the manufacturing phase

National production mix from import, low voltage (production of transmission lines, in addition to direct emissions and losses in grid) of applied electricity for the manufacturing process (A3).

Electricity mix	Data source	Amount	Unit
Electricity, Sweden (kWh)	ecoinvent 3.6	54,94	g CO2-eg/kWh

Dangerous substances

The product contains no substances given by the REACH Candidate list or the Norwegian priority list.

Indoor environment

Additional Environmental Information

Additional environmental impact indicators required in NPCR Part A for construction products											
Indicator	Unit	A1	A2	A3	A4	A5	C1	C2	C3	C4	D
GWPIOBC	kg CO ₂ -eq	2,29E-02	3,76E-02	6,11E-02	9,50E-03	0,00E+00	0,00E+00	1,01E-03	1,82E+00	9,19E-05	-1,02E-01

GWP-IOBC: Global warming potential calculated according to the principle of instantaneous oxidation. In order to increase the transparency of biogenic carbon contribution to climate impact, the indicator GWP-IOBC is required as it declares climate impacts calculated according to the principle of instantaneous oxidation. GWP-IOBC is also referred to as GWP-GHG in context to Swedish public procurement legislation.



Bibliography

ISO 14025:2010 Environmental labels and declarations - Type III environmental declarations - Principles and procedures.

ISO 14044:2006 Environmental management - Life cycle assessment - Requirements and guidelines.

EN 15804:2012+A2:2019 Environmental product declaration - Core rules for the product category of construction products.

ISO 21930:2017 Sustainability in buildings and civil engineering works - Core rules for environmental product declarations of construction products.

ecoinvent v3, Allocation, cut-off by classification, Swiss Centre of Life Cycle Inventories.

Iversen et al., (2021) eEPD v2021.09 Background information for EPD generator tool system verification, LCA.no Report number: 07.21 Vold, M. et al (2022): EPD generator for NPCR 012, Additional products, EPS and XPS, Background information for EPD generator application NPCR Part A: Construction products and services. Ver. 2.0. April 2021, EPD-Norge.

NPCR 012 Part B for Thermal insulation products, version 2, 31.03.2022, 2022., EPD Norway.

© epd-norway	Program operator and publisher	Phone: +47 23 08 80 00
epu-norway	The Norwegian EPD Foundation	e-mail: post@epd-norge.no
Global Program Operator	Post Box 5250 Majorstuen, 0303 Oslo, Norway	web: www.epd-norge.no
DEMAIL	Owner of the declaration:	Phone: +47 95 07 67 42
BFW/	Bewi Insulation Scandinavia	e-mail: svein.tore.larsen@jackon.no
	Sørkilen 3, 1621 GRESSVIK, Fredrikstad i VIKEN	web: www.jackon.no
	Author of the Life Cycle Assessment	Phone: +47 916 50 916
(LCA)	LCA.no AS	e-mail: post@lca.no
	Dokka 6B, 1671	web: www.lca.no
	Developer of EPD generator	Phone: +47 916 50 916
(LCA)	LCA.no AS	e-mail: post@lca.no
.no	Dokka 6B,1671 Kråkerøy	web: www.lca.no
ECO PLATFORM	ECO Platform	web: www.eco-platform.org
VERIFIED	ECO Portal	web: ECO Portal
CRITIED		